

**HIDDEN TEXT: Specifier Notes may be turned on throughout section as follows; click on "File" then on "Options" then "Display" and add check mark for "Hidden text" in two locations.**

## **Section 07 0543.32**

### **COMPOSITE METAL HYBRID (CMH) CONTINUOUS INSULATION CLADDING SUPPORT SYSTEMS**

#### **PART 1 – GENERAL**

##### **1.01 SECTION INCLUDES**

- A. Composite metal hybrid (CMH) sub-framing support system with in-fill continuous insulation integrated within [metal wall panels] [brick veneer] [CMU veneer] [phenolic panels] [fiber cement panels] [terracotta] or [<\_\_\_\_>] exterior wall cladding.
  - 1. Substrate: [Exterior sheathing over metal stud framing] [Exterior sheathing over wood stud framing] [Concrete masonry units (CMU)] or [Poured concrete].

##### **1.02 RELATED REQUIREMENTS**

- A. Section 03 3000 – Cast-in-Place Concrete: Concrete wall substrate.
- B. Section 04 2000 – Unit Masonry: Concrete masonry unit (CMU) wall substrate.
- C. Section 05 4000 – Cold-Formed Metal Framing: Metal stud substrate support framing.
- D. Section 06 1000 – Rough Carpentry: Exterior sheathing and wood stud substrate support framing.
- E. Section 07 2500 – Weather Barriers: Air, water, vapor barrier at exterior wall.
- F. Section 07 4200 – Wall Panels: Exterior wall panel system.
- G. Section 07 9200 – Joint Sealants: Perimeter sealant.
- H. Section 09 2116 – Gypsum Board Assemblies: Exterior wall sheathing.

##### **1.03 REFERENCE STANDARDS**

- A. ASCE American Society of Civil Engineers ([www.asce.org](http://www.asce.org)).
  - 1. ASCE 7 – Minimum Design Loads and Associated Criteria for Buildings and Other Structures; 2022.
  - 2. ASCE – Structural Plastics Design Manual.
- B. ASHRAE American Society of Heating, Refrigerating, and Air-Conditioning Engineers ([www.ashrae.com](http://www.ashrae.com)).
  - 1. ASHRAE 901 – Energy Standard for Buildings Except Low-Rise Residential Buildings; 2019.
  - 2. ASHRAE 189.1 – Standard for the Design of High-Performance Green Buildings Except Low-Rise Residential Buildings; 2020.
- C. ASTM International – American Society for Testing and Materials ([www.astm.org](http://www.astm.org)).
  - 1. ASTM A653/A653M – Standard Specification for Steel Sheet, Zinc-Coated (Galvanized) or Zinc-Iron Alloy-Coated (Galvannealed) by the Hot-Dip Process; 2022.
  - 2. ASTM C209 – Standard Test Methods for Cellulosic Fiber Insulating Board; 2020.
  - 3. ASTM C518 – Standard Test Method for Steady-State Thermal Transmission Properties by Means of Heat Flow Meter Apparatus; 2021.
  - 4. ASTM C754 – Standard Specification for Installation of Steel Framing Members to Receive Screw-Attached Gypsum Panel Products; 2020.
  - 5. ASTM C1177/C1177M – Standard Specification for Glass Mat Gypsum Substrate for Use as Sheathing; 2017.

6. ASTM C1289 – Standard Specification for Faced Rigid Cellular Polyisocyanurate Thermal Insulation Board; 2022a.
  7. ASTM C1363 – Standard Test Method for Thermal Performance of Building Materials and Envelope Assemblies by Means of a Hot Box Apparatus; 2019.
  8. ASTM C1396/C1396M – Standard Specification for Gypsum Board; 2017 (2022).
  9. ASTM D256 – Standard Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics; 2010 (2018).
  10. ASTM D570 – Standard Test Method for Water Absorption of Plastics; 2022.
  11. ASTM D635 – Standard Test Method for Rate of Burning and/or Extent and Time of Burning of Plastics in a Horizontal Position; 2022.
  12. ASTM D638 – Standard Test Method for Tensile Properties of Plastics; 2022.
  13. ASTM D696 – Standard Test Method for Coefficient of Linear Thermal Expansion of Plastics Between minus 30 degrees C and 30 degrees C with a Vitreous Silica Dilatometer; 2016.
  14. ASTM D790 – Standard Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials; 2017.
  15. ASTM D792 – Standard Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement; 2020.
  16. ASTM D1621 – Standard Test Method for Compressive Properties of Rigid Cellular Plastics; 2016.
  17. ASTM D2126 – Standard Test Method for Response of Rigid Cellular Plastics to Thermal and Humid Aging; 2020.
  18. ASTM D4385 – Standard Practice for Classifying Visual Defects in Thermosetting Reinforced Plastic Pultruded Products; 2019.
  19. ASTM D6641/D6641M – Standard Test Method for Compressive Properties of Polymer Matrix Composite Materials Using a Combined Loading Compression (CLC) Test Fixture; 2016e2.
  20. ASTM D7332-B – Standard Test Method for Measuring the Fastener Pull-Through Resistance of a Fiber-Reinforced Polymer Matrix Composite; 2022.
  21. ASTM E84 – Standard Test Method for Surface Burning Characteristics of Building Materials; 2022.
  22. ASTM E96/E96M – Standard Test Methods for Gravimetric Determination of Water Vapor Transmission Rate of Materials; 2022a.
  23. ASTM E119 – Standard Test Methods for Fire Tests of Building Construction and Materials; 2022.
  24. ASTM E330/E330M – Standard Test Method for Structural Performance of Exterior Windows, doors, Skylights and Curtain Walls by Uniform Static Air Pressure Difference; 2014 (2021).
- D. ICB – International Building Code (ICC – International Code Council); 2021.
- E. IECC – International Energy Conservation Code; 2021.
- F. IgCC – International Green Construction Code; 2021.
- G. NFPA – National Fire Protection Associate ([www.nfpa.org](http://www.nfpa.org)).
1. NFPA 285 – Standard Fire Test Method for Evaluation of Fire Propagation Characteristics of Exterior Wall Assemblies Containing Combustible Components; 2023.
- H. Voluntary Product Standard; Department of Commerce (DOC) and National Institute of Standards and Technology (NIST) ([www.apawood.org](http://www.apawood.org)).
1. PS 1 – Structural Plywood; 2019 (Revised 2020).

#### 1.04 ADMINISTRATIVE REQUIREMENTS

- A. Coordinate installation of continuous insulation sub-framing support system as indicated on drawings for proper drainage, flashing, trim, backup support, soffits, and other related Work.
1. Review and finalize construction schedule.
  2. Verify availability of materials, installer's personnel, equipment, and facilities needed to meet established schedule.

PROJECT NO.:  
DATE:

PROJECT NAME  
PROJECT LOCATION

3. Review means and methods related to installation in accordance with manufacturer's installation instructions.
4. Examine support conditions for compliance with installation requirements, including alignment and attachment to structural support system.
5. Review flashings, wall cladding details, wall penetrations, drainage plane, openings, and condition of other construction that is related to this Work.
6. Review temporary protection requirements for during and after installation of this Work.

#### 1.05 SUBMITTALS

- A. See Section 01 3000 – Administrative Requirements for submittal procedures.
- B. Product Data: Submit for each product being used as indicated, including installation details, material descriptions, dimensions of individual components and profiles, and necessary accessories for a complete assembled system.
- C. Test and Engineering Reports: Submit Test and Engineering reports on each type of composite sub-framing system based on the evaluation of comprehensive tests performed by a certified testing agency and/or Professional Engineers (PE) approved by authorities having jurisdiction.
  1. Structural Composite Sub-Framing Submittal:  
Provide PE stamped calculations for the composite sub-framing system carrying the associated cladding system that takes into account:
    - a. Anisotropic properties of the sub-framing.
    - b. Point loading of the fasteners and representative dynamics of the cladding system.
    - c. Uniform loading calculations not being allowed as it is not representative to actual wall systems.
    - d. Calculations for eccentric cantilever conditions.
    - e. Calculations providing a safety factor minimum of 4 at the high service temperature of 180 degrees Fahrenheit.
    - f. Fastener Creep and Durability Test for FRP sub-girts, certified by third party/PE. Test to be completed per reference section 2.03E.
    - g. Fire: ASTM E84 Class A and NFPA 285 tested for the specific wall assembly in this project.
- D. Warranty: Submit manufacturer's sample warranty and ensure forms have been completed in Owner's name, registered with manufacturer for the Manufacturer's Warranty for the Sub-Framing System, and FRP Manufacturer's Warranty for Screw Creep and Durability per section 1.09.

#### 1.06 QUALITY ASSURANCE

- A. Manufacturer Qualifications: Company specializing in manufacturing products specified in this section with at least ten years of documented experience.
  1. Engineering Review: Manufacturer to provide Technical Engineering Report (TER) based on CMH support system and cladding system design.
  2. Code Conformance: CMH system to have been evaluated by IAPMO Uniform Evaluation Service and found satisfactory for compliance with 2018 International Building Code.
- B. Installer Qualifications: Company specializing in performing work as indicated in this section with at least three years of documented experience and approved by manufacturer.
  1. Install system in strict compliance with manufacturer's installation instructions.
- C. Design Engineer's Qualification: Design structural supports and anchorages under direct supervision of a licensed Structural Engineer experienced in design for this type of Work and licensed in State that Project is located. Engineering information provided shall be signed and verified by licensed Structural Engineer.

PROJECT NO.:  
DATE:

PROJECT NAME  
PROJECT LOCATION

- D. Source Limitations: Obtain continuous insulation (CI) and CMH support system from single source and single manufacturer.
- E. Environmental: CMH system to follow the below guidelines:
  - 1. CMH system to be registered as red list chemical free with the Declare label.
  - 2. The components shall be certified to be halogen/bromine free.
  - 3. CMH composite member shall utilize a minimum of 25% post-consumer recycled material content.
  - 4. Environmental Product Declaration: CMH Manufacturer shall provide a product-specific EPD Type III report in accordance with EN 15804 and ISO 14025.

## **1.07 DELIVERY, STORAGE, AND HANDLING**

- A. See Section 01 7419 – Construction Waste Management and Disposal for material waste requirements.
- B. Deliver materials to site without damage or deformation in manufacturer's original unopened containers and with labels that clearly identify product name and manufacturer.
- C. Storage: Store materials in clean, dry, and level interior or exterior areas for limited duration in accordance with manufacturer's written instructions.
- D. Protect components during transportation, handling, and installation from moisture, excessive temperatures, and other construction operations in accordance with manufacturer's written instructions.
- E. Handle components in accordance with manufacturer's written instructions and in a manner to prevent bending, warping, twisting, and surface, edge, or corner damage.

## **1.08 SITE CONDITIONS**

- A. Weather Limitations: Only proceed with installation when existing and forecasted weather conditions allow for assembly of this Work in accordance with manufacturer's written installation instructions.

## **1.09 WARRANTY**

- A. See Section 01 7800 – Closeout Submittals for additional warranty requirements.
- B. Manufacturer's Warranty for the Sub-Framing System: Provide five (5)-year manufacturer's warranty for composite metal hybrid (CMH) sub-framing support system commencing on the date of manufacture or date of substantial completion.
- C. FRP Manufacturer's Warranty for Screw Creep and Durability: Provide 20-year manufacturer's non-prorated, product replacement warranty against fastener creep and/or decreased fastener retention capacity for cladding fasteners that are anchored solely into an FRP substrate in lieu of a metal substrate. FRP material to be warrantied to perform long term to retain fasteners in a load capacity equivalent to 16 Ga. steel under the same loading, temperature, duration, and durability.

## **PART 2 – PRODUCTS**

### **2.01 MANUFACTURER**

PROJECT NO.:  
DATE:

PROJECT NAME  
PROJECT LOCATION

- A. Advanced Architectural Products (A2P):
  - 1. Address: 959 Industrial Drive, Allegan, Michigan 49010.
  - 2. Phone: (269) 355-1818; Fax: (866) 858-5568; Website: GreenGirt.com.
- B. Products:
  - 1. GreenGirt CMH Sub-Framing System.
  - 2. SMARTci 2.5 in 1 System.
  - 3. SMARTci 3 in 1 System.
  - 4. Other products shall be pre-submitted and approved products that meet materials and performance requirements with specified and validated third-party testing.

## 2.02 DESCRIPTION

- A. Attach CMH sub-framing support system components **[through exterior sheathing into metal stud framing] [through exterior sheathing into wood stud framing] [into open metal framing] [to concrete masonry units (CMU)] or [to poured concrete wall]** as indicated on drawings.
  - 1. See Section 03 3000 for concrete substrate.
  - 2. See Section 04 2000 for CMU substrate.
  - 3. See Section 05 4000 for metal stud framing.
  - 4. See Section 06 1000 for **[exterior sheathing]** and/or **[wood stud framing]**.
  - 5. See Section 07 4200 for wall panels system.
- B. Install CMH sub-framing support system components **[horizontally]** through exterior sheathing into stud support system as indicated on drawings in compliance with project requirements.
- C. Install CMH sub-framing support system components **[horizontally]** onto **[masonry]** or **[concrete]** substrate system with shims as indicated on drawings in compliance with project requirements.
- D. If necessary, install metal hat channel as indicated on drawings, mounted or **[vertically to horizontal]** CMH sub-framing support system, connecting adjacent supports in series to each other.

## 2.03 PERFORMANCE REQUIREMENTS

- A. Structural Performance: Provide system tested in accordance with ASTM E330/E330M and certified to be without permanent deformation or failure of structural members in accordance with design wind velocities for project location and potential for occurrence based on data from wind velocity maps and other provisions of ASCE 7 and as approved by authorities having jurisdiction (AHJ).
  - 1. Provide finite element analysis (FEA) to model and evaluate areas of the longest composite girt cantilever span possible between intermediate framing members/attachment.
    - a. FEA Shall include maximum dead load and wind load conditions.
    - b. FEA shall include point loads representative of fastener locations.
    - c. Maximum directional stresses in model shall have a safety factor of 4 or greater.
    - d. Stresses shall be indicated and analyzed in 3 directions.
    - e. FEA shall accurately replicate the wall system and physical loading dynamics.
    - f. Report shall be furnished with the submittal.

PROJECT NO.:  
DATE:

PROJECT NAME  
PROJECT LOCATION

2. Butt joints (non-interlocking joints) of adjacent girts shall be installed on a minimum surface width of 3" or double stud condition to accommodate proper fastener margins to composite.
- B. System Thermal Design: Ensure that installed continuous insulation and CMH sub-framing support system, and cladding attachment does not have thermal bridging of fasteners or framing that creates a continuous metal path from exterior surface of insulation to interior face of insulation.
1. Verify that system thermal design meets or exceeds thermal design requirements in accordance with [ASHRAE 90.1] [ASHRAE 189.1] [IECC] or [IgCC] energy code.
  2. Thermal Resistance, Overall: Provide wall assembly R-Value of [ $< \_\_\_\_\_\_ >$ ], minimum.
  3. Thermal Performance Test: Provide thermal resistance (R-value) indicated, in accordance with ASTM C1363, corrected to 15 mph wind outside and still air inside, with installed condition including fasteners and joints.
  4. Provide efficiency of no less than [93 to 98 percent] or [ $< \_\_\_\_\_\_ >$  percent], with a maximum temperature differential of 18 degrees F from interior wall surface to interior wall cavity and node locations with a 70 degrees F exterior to interior wall temperature delta.
  5. Provide test unit with at least one insulation panel horizontal and vertical joint length and height of test chamber area.
  6. Provide finite element analysis of three-dimensional simulation of described wall assembly sealed by a professional engineer in compliance with code performance requirements and exceeding it by at least 3 percent.
- C. Temperature Range: Comply with structural loading requirements within a temperature range of minus 55 degrees F to 180 degrees F.
- D. Fire-Resistance Ratings: Provide CMH sub-framing support system with fire testing in accordance with ASTM E119 test methods and applied by approved testing agency acceptable to authorities having jurisdiction (AHJ).
1. Surface Burning Characteristics: Test in accordance with ASTM E84 test method for continuous insulation, composite metal hybrid (CMH) and interior surfaces as follows:
    - a. Flame Spread Index (FSI): 25 or less.
    - b. Smoke Developed Index (SDI): 450 or less.
  2. Intermediate Scale Multistory Fire Test: Comply with NFPA 285 and/or IBC acceptance criteria for wall height above grade and fire separation distances when wall type and other noted conditions require such testing or compliance with requirements as indicated.
- E. Fastener Creep and Durability Test: For fasteners anchored into an FRP substrate without metal backer/retention system, perform per ASTM D7332-B, seven (7) day continuous fastener loading at the project's specified high service temperature of 180 degrees F.
1. The fastener thread pull-out test is to be performed for self-drilling screws anchored solely into an FRP substrate. Test with ASTM D7332-B fixture using a fixture with a clearance opening of 34mm (1.313") in diameter. The pulling yoke is to be attached to the fastener head, with the load transferring into the anchoring threads. Ramp loading for no less than 30 seconds and no more than 120 seconds.

PROJECT NO.:  
DATE:

PROJECT NAME  
PROJECT LOCATION

2. Testing to be performed inside a climate chamber at a temperature of 180 degrees F for a period of 7 days at ultimate fastener load. Passing load values to be considered ultimate pull-out values for project engineering purposes.
3. Test for 5 samples at same loading and temperature without pull-out. Testing to be certified by independent 3rd party.
4. Test results of fastener head/thread pull-through performed at room temperature with static ASTM D7332-B are not considered valid for creep and durability testing and are not to be used for determining ultimate screw loading values.

## **2.04 COMPOSITE METAL HYBRID (CMH) SUB-FRAMING SUPPORT SYSTEM**

- A. CMH Sub-Framing Support System: Provide CMH sub-framing support system with recycled materials, fire retardant additives, and integral continuous metal inserts the length of the profile. Reinforce CMH sub-framing support system with glass strand rovings used internally for longitudinal (lengthwise) strength and continuous strand glass mats or stitched reinforcements used internally for transverse (crosswise) strength.

1. Length of CMH Support System: 96 inches standard length.
2. Depth of CMH Support System: [2 inches] [2-1/2 inches] [3 inches] [3-1/2 inches] or [4 inches] deep.
3. Grid Spacing of CMH Sub-Framing Supports for Horizontal Substrate Attachments:
  - a. Horizontal Spacing: [16 inches] or [24 inches] or center.
4. Fastener Retention System: Provide continuous galvanized steel insert for engagement of fasteners, at least 16 gauge thick, with G90 galvanized coating in accordance with ASTM A653/A653M.
  - a. Fasten CMH sub-framing support and other wall cladding support accessories through steel insert located within top and bottom of CMH sub-framing.
  - b. Provide screw pullout testing that meets or exceeds [< \_\_\_lbs>].
  - a. Provide at least 3-inch overlap of metal inserts between CMH supports with 1/16 inch wide gap; sealant is not required.
5. Provide integral compression seal with CMH sub-framing to ensure insulation will not dislodge.
6. Provide integral anti-siphon grooves on exterior and interior flanges of CMH sub-framing.
7. Provide force distribution zones integrally designed into profile of CMH sub-framing.
8. CMH sub-framing is self-extinguishing in accordance with ASTM D635.
9. Visual defects in CMH sub-framing is classified in accordance with ASTM D4385.
10. Tensile Properties: Engineered lengthwise and crosswise tensile properties of CMH sub-framing comply with performance loading criteria and specified safety factors in accordance with ASTM D638.
  - a. Lengthwise 50,000 psi and crosswise 40,000 psi, minimum.
11. Compressive Properties: Engineered lengthwise and crosswise compressive properties of CMH sub-framing comply with performance loading criteria and specified safety factors in accordance with ASTM D6641/D6641M.
  - a. Lengthwise 50,000 psi and crosswise 30,000 psi, minimum.

12. Flexural Properties: Engineered lengthwise and crosswise flexural properties of CMH sub-framing comply with performance loading criteria and specified safety factors in accordance with ASTM D790.
  - a. Lengthwise 50,000 psi and crosswise 40,000 psi, minimum.
13. Modulus of Elasticity: CMH sub-framing is engineered to meet performance loading criteria and specified safety factors in accordance with ASTM D638.
  - a. Lengthwise 29,000,000 psi and crosswise 3,300,000 psi, minimum.
14. Water Absorption: CMH sub-framing absorbs less than 0.46 percent by weight within 24 hours when tested in accordance with ASTM D570.
15. Relative Density: CMH sub-framing is within range of 0.062 to 0.070 lbs/cubic inch when tested in accordance with ASTM D792.
16. Coefficient of Linear Thermal Expansion: CMH sub-framing is at  $7.0 \times 10^{-6}$  inch/inch/degrees F when tested in accordance with ASTM D696.
17. Notched Izod Pendulum Impact Resistance, Lengthwise: CMH sub-framing is at 160 ft lbs/inch when tested in accordance with ASTM D256 within standard temperature range.
18. Notched Izod Pendulum Impact Resistance, Crosswise: CMH sub-framing is at 100 ft lbs/inch when tested in accordance with ASTM D256 within standard temperature range.
19. Barcol: Hardness: 45, in accordance with ASTM D2583.
20. Surface Burning Characteristics:
  - a. Flame Spread Index (FSI): 25 or less, when tested in accordance with ASTM E84.
  - b. Smoke Developed Index (SDI): 450 or less, when tested in accordance with ASTM E84.
21. Flammability: Comply with ASTM E84.
22. Provide spline seals for adjacent insulation units into profile of CMH sub-framing.
23. Thermal Transmission: CMH sub-framing support system design should limit rate of heat flow crosswise through the profile section to less than [ \_\_\_\_\_ ] watts per 8' length in profile and temperature delta of 100 degrees Fahrenheit. Rate of heat flow to be determined in accordance with ASTM C1045-01, validated by a third party.

#### REFERENCE CHART

Profile Depth	Rate of heat flow (watts)
1.5"	2.380W
2"	1.785W
2.5"	1.428W
3"	1.190W
3.5"	1.020W
4"	0.892W
4.5"	0.793W

PROJECT NO.:  
DATE:

PROJECT NAME  
PROJECT LOCATION

<b>5"</b>	<b>0.714W</b>
<b>5.5"</b>	<b>0.649W</b>
<b>6"</b>	<b>0.595W</b>

## 2.05 INSULATION

- A. Insulation Panel Edges: Provide factory-formed edges on insulation panels that interlock with CMH system components.
- B. Polyisocyanurate Panel Insulation: Rigid closed cell foam, complying with ASTM C1289; Type I with impermeable aluminum foil facing on both sides; Class 1 with non-reinforced foam core.
1. Surface Burning Characteristics:
    - a. Flame Spread Index (FSI): 25 or less when tested in accordance with ASTM E84.
    - b. Smoke Developed Index (SDI): 25 or less when tested in accordance with ASTM E84.
  2. Board Size: **[16 by 48 inches] [24 by 48 inches] or [( ) by ( ) inches]**.
  3. Thickness: **[2 inches] [2-1/2 inches] [3 inches] [3-1/2 inches] [4 inches] or [( ) inches]**.
  4. Thermal Resistance: **[1-1/2 inch, R-Value 9.5] [2 inch, R-Value 13] [2-1/2 inch, R-Value 16] [3 inch, R-Value 19] [3.5 inch, R-Value 22] or [4 inch, R-Value 25];** ASTM C518 at 75 degrees F. - R-values reported by Hunter (BOD).
  5. Comply with fire-resistance requirements, as indicated on drawings, and as part of an exterior non-load-bearing exterior wall assembly, testing in accordance with NFPA 285.
  6. Board Edges: Square.
  7. Compressive Strength: **[Grade 1, 16 psi] [Grade 2, 20 psi] or [Grade 3, 25 psi]** when tested in accordance with ASTM D1621.
  8. Dimensional Stability: Less than 2 percent linear change after 7 days when tested in accordance with ASTM D2126.
  9. Water Vapor Permeance: Less than 0.05 perm when tested in accordance with ASTM E96/E96M.
  10. Water Absorption: Less than 0.05 percent by volume when tested in accordance with ASTM C209.
  11. Service Temperature: Range of minus 100 degrees F to 250 degrees F.
  12. Acceptable Products:
    - a. Hunter Panels, LLC; Product Hunter Xci Foil (Class A) ([www.hunterpanels.com](http://www.hunterpanels.com)).
    - b. DuPont; Product DuPont Thermax Sheathing ([www.dupont.com](http://www.dupont.com)).
    - c. Atlas Polyiso Roof & Wall Insulation, a Division of Atlas Roofing Corporation; Product EnergyShield Pro ([www.atlasrwi.com](http://www.atlasrwi.com)).
    - d. Elevate, formerly Firestone; Product Enverge CI Foil Exterior Wall Insulation ([www.holcimelevate.com](http://www.holcimelevate.com)).
    - e. Substitutions: See Section 01 6000 – Product Requirements.

## 2.06 COMPOSITE METAL HYBRID (CMH) TRIM

- A. CMH Trim: Provide nonstructural trim at rough openings to properly transition continuous insulation (CI) system.
1. Use angled and flat trim to enclose CI system and to provide thermally broken transitions within wall assemblies.
    - a. Angled Trim: **[2 by 3 inches] and/or [4 by 6 inches] or [As indicated on drawings]**.
    - b. Flat Trim: **[6 inches] and/or [12 inches] wide, or [As indicated on drawings]**.
  2. Use sealant and tapes as required to transition weather-resistive barriers (WRB) from substrate onto trim.
  3. Trim to provide 90-degree transition of CI substrate for weather-resistive barriers (WRB) and exterior flashing.
  4. Cover trim with exterior panel assembly and flashings.

PROJECT NO.:  
DATE:

PROJECT NAME  
PROJECT LOCATION

5. Surface Burning Characteristics:
  - a. Flame Spread Index (FSI): 25 or less when tested in accordance with ASTM E84.
  - b. Smoke Developed Index (SDI): 450 or less when tested in accordance with ASTM E84.
6. Comply with fire-resistance requirements, as indicated on drawings, and as part of an exterior non-load-bearing exterior wall assembly, tested in accordance with NFPA 285.
7. Water Absorption: Less than 0.46 percent by weight, within 24 hours, tested in accordance with ASTM D570.
8. Acceptable Products:
  - a. SMARTci Trim
  - b. Alternative: Performance CI system utilizing metal trim to provide spray foam insulation at a depth of 6" extending 32" around openings to reduce thermal transfer at wall transitions.

## 2.07 ASSEMBLY

- A. Assemble CMH sub-framing support system in accordance with manufacturer's installation instructions and as necessary to comply with performance requirements indicated.
  1. Comply with CMH sub-framing support system dimensional and structural requirements as indicated on drawings.
  2. Install CMH sub-framing support system in acceptable sequence in accordance with manufacturer's written installation instructions.
  3. Install spray foam sealant on backside of cantilevered fasteners that completely puncture insulation layer.
  4. Provide uninterrupted, monolithic drainage plane as required per project details.

## 2.08 ACCESSORIES

- A. Provide necessary accessories for complete installation of CMH sub-framing support system including **[metal closure trim] [transition angle] [strapping] [tie-in brackets]** or **[<\_\_\_\_>]**, and other similar items.
- B. Fasteners: Corrosion-resistant, self-tapping and self-drilling screws, bolts, nuts, and other fasteners as recommended by CMH sub-framing support system manufacturer for CMH materials and other project applications.
  1. Cladding to CMH: Use standard self-tapping metal screws.
  2. CMH to Metal Stud Wall Framing: Use standard self-tapping metal screws.
  3. CMH to Concrete or Concrete Masonry Units (CMU): Use standard masonry or concrete screw anchors in pre-drilled hole.
  4. CMH to Wood Stud Wall Framing: Use standard wood screw anchors.
  5. Use of powder, air, or gas-actuated fasteners or actuated fastener tools is not permitted.
  6. Use of impact wrenches when fastening to or from CMH is not permitted.
  7. CMH attachments to follow guidelines of ASCE Structural Plastics Design Manual:

	Ratio of distance to fastener diameter
	Minimum Distance Allowable
Edge distance- end	3.0
Edge distance- side	2.0

- C. Wall Sheathing: Plywood; Grade C-D and Exposure I in accordance with Voluntary Product Standard PS I.
  1. Refer to drawings for thickness and see Section 06 1000 for additional requirements.

PROJECT NO.:  
DATE:

PROJECT NAME  
PROJECT LOCATION

- D. Wall Sheathing: Gypsum board; V-shaped long edges and Type X fire-resistant in accordance with ASTM C1396/C1396M.
  - 1. Refer to drawings for thickness and see [Section 06 1000] or [Section 09 2116] for additional requirements.
- E. Tape (if necessary): Pressure-sensitive adhesive-coated polypropylene woven fabric. Must be mold, water, tear and UV resistant. Must be applicable in a wide temperature range (-20 degrees F).
- F. Weather-Resistive Barriers (WRB): See Section 07 2500 for additional information.
- G. Sealants (if necessary): See Section 07 9200 for additional information.
- H. Closure and Transition Accessories (if necessary): Use [metal] or [FRP] angles and flat stock per standard system details.

### **PART 3 – EXECUTION**

#### **3.01 EXAMINATION**

- A. Examine areas of this Work, substrates, and other project conditions with installer present to verify compliance with requirements for installation tolerances, substrates, CMH sub-framing support system conditions, and other conditions relating to this Work.
- B. Examine structural wall framing to ensure that angles, channels, studs, and other structural support members have been installed within alignment tolerances in accordance with installation instructions of CMH sub-framing support system manufacturer.
- C. Examine components and systems penetrating CMH sub-framing support system prior to installation during rough-in stage of construction to coordinate actual locations of penetrations relative to CMH sub-framing support system's joint locations.
- D. Verify that mechanical and electrical-related installations for exterior walls have been completed and verify that adjacent materials and finishes are dry and ready for insulation installation.
- E. Proceed with installation of CMH sub-framing support system only after wall substrate surfaces have been properly prepared and unsatisfactory conditions have been corrected.

#### **3.02 PREPARATION**

- A. Clean surfaces thoroughly prior to installation.
- B. Prepare substrate surfaces using methods recommended in writing by CMH sub-framing support system manufacturer to achieve excellent results under project conditions.
- C. Prepare sub-framing, base angles, sills, furring, and other CMH sub-framing support system components and provide anchorage in accordance with ASTM C754 for substrate and wall cladding types in accordance with manufacturer's installation instructions.

#### **3.03 INSTALLATION**

- A. Install CMH sub-framing support system in accordance with manufacturer's installation instructions.
- B. Install CMH sub-framing support system to meet requirements of ASCE Structural Plastics Design Manual.
- C. Install system to fill-in exterior spaces without gaps or voids, and do not compress insulation panels.

PROJECT NO.:  
DATE:

PROJECT NAME  
PROJECT LOCATION

- D. Trim insulation neatly to fit spaces and insulate miscellaneous gaps and voids.
- E. Fit insulation tight in spaces and tight to exterior side of Mechanical/Electrical services within plane of insulation.
- F. Seal gaps, voids or penetrations completely with approved expandable foam sealant on exterior and interior (if visible) before enclosing wall.
- G. Provide spray foam to seal metal penetrations, including cantilevered fasteners, to prevent interstitial space condensation.
- H. Exposed insulation must be protected from open flame and kept dry at all times.
- I. Exterior wall insulation panels are not intended to be left exposed for periods of time to excess of 60 days without adequate protection.
  - 1. When extended exposure is anticipated, protect exposed insulation surfaces including corners, windows and door openings with a compatible waterproof tape.
- J. Install CMH sub-framing support system in compliance with system orientation, sizes, and locations as indicated on drawings.

#### **3.04 TOLERANCES**

- A. Shim and align CMH sub-framing support system with installation tolerances of 1/4 inch in 20 feet, non-cumulative, level, plumb, and aligned with locations as indicated on drawings.

#### **3.05 PROTECTION**

- A. Protect installation products from damage until Date of Substantial Completion.
- B. Ensure that insulation panels are not exposed to moisture.
  - 1. Remove wet insulation panels or allow them to completely dry prior to installation within CMH sub-framing support system.
- C. Replace damaged insulation prior to Date of Substantial Completion.

**END OF SECTION**